

LABORATORY RESULT NOTIFICATION FORM

COMPANY	PRODUCT	DATE: 20.3.2019 0:00			OPTICAL MEASUREMENT			TESTS	
		%LT Light TRANSMISSION 400-700 nm	%LD Diffused TRANSMISSION 400-700 nm	%UV TRANSMISSION 300-380 nm	MFI g/10min	ENDURANCE	PULL/BREAKING ELONGATION		
COVERNA 2F AGRIPOLYANE	200 MIC YELLOW	77	38	1,13	0,31	MD 17,79	TD 18,15	458	645
VATAN PLASTIC	200 MIC YELLOW	77	45	2,30	0,48	MD 22,87	TD 20,16	571	779
LABORATORY MANAGER: SELAHATTİN KOÇAK									